VOC COMPLIANT LACQUER THINNER	TECHNICAL DATA SHEET	477

SUNNYSIDE VOC COMPLIANT LACQUER THINNER

DESCRIPTION

VOC Compliant Lacquer Thinner is the recommended lacquer thinneer and clean up solvent when a low VOC thinner is required. Fast evaporating and extremely flammable.

SAFETY INFORMATION

HEALTH: 2
FIRE: 3
REACTIVITY: 1

ITEM NUMERS & SIZES

Pint	Quart	1-Gallon	2.5-Gal.	5-Gal.	55-Gal.
	47732	477G1		477G5	

HAZARDOUS INGREDIENTS

Ingredient	CAS#
Acetone	67-64-1
Parachlorobenzo-trifluoride	98-56-6
2-Butoxyethanol	111-76-2

PRODUCT APPLICATION

VOC Compliant General Purpose Thinner effectively thins most oil based paints, stains and varnishes. Use for clean up after painting.

PHYSICAL PROPERTIES

Typical Properties	Results
GRAVITY, (60 ˚F)	
API	
SPECIFIC	0.85
DENSITY (Lb./GAL)	7.08
DISTILLATION RANGEE IBP ° F	133
FREEZING POINT, ˚F (˚C)	
KAURI BUTANOL (Kb) VALUE	
ANILINE POINT, ˚F	
FLASH POINT, T.C.C. ˚F	0
FLAMMABLE LIMITS IN AIR, % BY VOLUME	
LOWER, AT 100˚F (38˚C)	
UPPER, AT 200˚F (93˚C)	
AUTOIGNITION TEMPERATURE, ˚F (˚C)	
COLOR (Pt t-Co) Max.	5
DOCTOR TEST	
CORROSION, 3 HRS. @ 212 ˚F	
NON-VOLATILES, g/100ml	
ACIDITY (as Acetic Acid)	
ALKALINITY (AS NH3, WT%)	
EVAPORATION RATE	Slower than ether
APPEARANCE	Clear, water-white
ODOR	Characteristic, Nonresidual
VAPOR PRESSURE, mm Hg @ 20 ˚C	
REFRACTIVE INDEX, @ 20 ˚C	
SULFUR CONTENT, PPM	
PURITY, by G.C., Wt%	
WATER CONTENT, Wt%	
WATER MISCIBILITY	Partial
DOT SHIPPING NAME	Paint related material
DOT CLASSIFICATION	Hazard Class III
SHIPPING Wt. at 20 ˚C	7.08
V.O.C. (g/L)	24 g/L

TEST METHOD

	ASTM	Applied
	D-278	
	D-1298	∎
		∎
	D-86	
	D-1133	
	D-611	
	D-56	∎
	D-1255	
	D-156	∎
	D-484	
	D-130	
	D-1353	
	D-847	
	D-1614	
	D-1296	∎
	D-1218	
	D-1266	
	D-1364	
	D-1722	

These properties are repesentative of typical inspections. They do not constitute product specifications. Consult MSDS sheet for additional information.

See MSDS sheet for additional Health, Safety, Handling and Regulatory Information available on our website at www.sunnysidecorp.com/msds.html